

AGI 0 2 熔融粘度

剪断速度 1/sec

粘度 Pa/sec

agi02-Roundhole=20.0/1.0/180

せん断速度	粘度				
	1 8 0	2 0 0	2 2 0	2 4 0	2 6 0
10.0224	37775.7	15841.4			
20.0448	27417.8	13404.3	7311.42		
39.9744	18331.2	10082.2	5804.89	3360.72	
99.9936	10381.7	6229.03	3908.41	2564.89	1587.79
199.987	6656.51	4091.62	2748.1	1893.14	1282.45
399.974	4274.82	2656.5	1832.07	1312.98	946.568
1000.05	2308.14	1453.27	1025.84	769.379	598.406
1999.99	1459.46	922.087	653.399	494.629	396.925
3999.97	922.087	574.014	418.298	314.487	256.475
10000.1	520.271	312.651		175.866	140.449

