

H9152熔融粘度

剪断速度 1/sec

粘度 Pa/sec

h9152-Roundhole=20.0/1.0/180

せん断速度	粘度				
	1 8 0	2 0 0	2 2 0	2 4 0	2 6 0
10	60929	30464			
20	39604	22544			
40	25969	14971	8860	6110	
100	14168	8428	5496	4031	2809
200	8855	5435	3664	2748	2015
400	5618	3450	2351	1771	1374
1000	3065	1820	1282	977	782
2000	1954	1130	800	617	495
4000	1249	699	492	388	311
10000	702	388	264	205	170

