

VS55熔融粘度

剪断速度 1/sec

粘度 Pa/sec

vs55-Roundhole=20.0/1.0/180

せん断速度	粘度				
	1 8 0	2 0 0	2 2 0	2 4 0	2 6 0
10					
20	24371	12795	6702		
40	16804	9777	5805	3361	
100	9649	5985	3908	2565	1588
200	6168	3908	2687	1893	1282
400	3939	2473	1771	1313	947
1000	2137	1368	989	757	574
2000	1350	867	629	482	379
4000	867	537	394	308	244
10000		294	211	169	133

