

# VS712溶融粘度

剪断速度 1/sec

粘度 Pa/sec

vs712-Roundhole=20.0/1.0/180

せん断速度	粘度				
	1 8 0	2 0 0	2 2 0	2 4 0	2 6 0
10	74333	42650	24371	15841	
20	46306	29246	18888	12795	
40	28413	18637	13137	9471	6416
100	15023	9893	7450	5740	4275
200	9160	6168	4580	3664	2931
400	5649	3786	2840	2290	1863
1000	2992	1966	1490	1197	989
2000	1887	1191	904	733	605
4000	1191	727	547	446	369
10000		396	287	211	193

