


# H 8 6 7 2 の曲げクリープ試験


2 3



2 3

	13.6MPa	18.1MPa	22.7MPa
0.02	6.3	9.5	12.1
0.05	6.7	9.7	12.8
0.10	6.7	9.5	13.3
0.15	6.7	9.6	13.7
0.50	6.8	9.7	14.9
1	6.8	9.8	15.9
2	6.9	10.0	17.0
4	7.0	10.3	18.6
8	7.1	10.6	20.8
20	7.4	11.3	25.2
40	7.6	11.9	30.6
100	8.0	12.9	42.0
200	8.5	14.0	64.6
300	8.8	14.8	


4 0



4 0

	7.7MPa	11.6MPa	15.4MPa
0.02	3.2	5.7	7.8
0.05	3.4	5.8	7.9
0.10	3.5	5.8	8.0
0.15	3.5	5.9	8.1
0.50	3.6	6.0	8.4
1	3.7	6.2	8.7
2	3.9	6.5	9.4
4	4.1	6.9	10.3
8	4.4	7.5	11.7
20	5.1	7.7	14.4
40	5.9	10.2	17.4
100	7.4	12.9	22.4
200	9.0	15.3	25.8
300	10	16.9	

6 0



60

	3.0MPa	4.5MPa	6.0MPa
0.02	0.9	1.8	2.7
0.05	1.0	1.8	2.9
0.10	1.0	1.9	2.9
0.15	1.1	2.0	3.0
0.50	1.5	2.9	3.7
1	2.1	4.7	5.0
2	3.2	5.9	7.5
4	4.6	7.6	10.6
8	6.0	9.4	13.7
20	7.8	12.0	17.7
40	9.2	14.0	20.6
100	11.1	16.6	24.5
200	12.5	18.6	
300	13.3	19.6	