


H 9 1 5 2 の曲げクリープ試験


2 3



2 3

	15.8MPa	21.0MPa	26.3MPa
0.02	6.9	9.7	12.0
0.05	6.9	9.7	12.5
0.10	6.9	9.8	13.0
0.15	6.9	9.8	13.3
0.50	6.9	10.1	14.9
1	6.9	10.3	15.9
2	6.9	10.6	17.6
4	6.9	11.0	19.5
8	6.9	11.6	22.7
20	7.0	12.6	28.6
40	7.7	13.6	35.6
100	7.8	15.4	48.4
200	8.0	17.2	64.3
300	8.2	18.6	69.0


4 0



4 0

	8.8MPa	13.3MPa	17.7MPa
0.02	3.7	6.1	8.2
0.05	3.7	6.1	8.3
0.10	3.7	6.1	8.4
0.15	3.7	6.1	8.4
0.50	3.7	6.1	8.9
1	3.7	6.5	9.3
2	3.7	6.5	10.1
4	4.2	6.9	11.5
8	4.2	7.4	12.9
20	4.8	8.4	16.7
40	5.8	10.3	20.7
100	7.0	12.9	27.6
200	8.3	15.1	32.4
300	9.1	16.6	

6 0



6 0

	3.4MPa	5.1MPa	6.8MPa
0.02	0.8	1.9	2.6
0.05	0.8	1.9	2.6
0.10	0.8	1.9	2.6
0.15	0.8	1.9	2.6
0.50	0.8	2.6	3.0
1	1.2	3.8	3.6
2	2.0	4.8	5.3
4	3.1	6.3	8.0
8	4.2	7.8	10.5
20	6.0	10.3	13.9
40	7.0	11.8	16.5
100	8.2	14.1	19.6
200	9.4	16.2	
300	10.2	16.8	