



V S 5 1 曲げクリープ試験




2 3

	10.5MPa	14.0MPa	17.6MPa
0.02	4.6	6.5	9.0
0.05	4.7	6.5	9.5
0.10	4.7	6.5	9.8
0.15	4.7	6.5	10.1
0.50	4.7	6.5	11.5
1	4.7	6.5	12.2
2	4.7	6.5	13.4
4	4.7	7.2	14.7
8	4.7	7.2	16.6
20	4.7	8.0	19.9
40	4.7	8.0	23.9
100	5.4	8.8	31.0
200	5.4	10.3	37.3
300	5.7	10.3	



4 0

	6.0MPa	9.1MPa	12.1MPa
0.02	2.4	4.0	5.9
0.05	2.5	4.1	6.0
0.10	2.6	4.1	6.0
0.15	2.6	4.2	6.1
0.50	2.7	4.3	6.5
1	2.8	4.5	6.9
2	2.9	4.7	7.6
4	3.1	5.0	8.4
8	3.4	5.4	9.6
20	4.1	6.6	12.1
40	4.9	7.9	14.9
100	6.3	10.4	19.9
200	7.8	12.6	23.3
300	8.7	14	



6 0

	2.3MPa	3.4MPa	4.6MPa
0.02	0.3	1.0	1.6
0.05	0.4	1.2	1.7
0.10	0.4	1.2	1.8
0.15	0.5	1.3	1.9
0.50	0.9	2.5	2.6
1	1.8	4.9	4.3
2	3.3	6.5	7.7
4	4.9	8.4	11.5
8	6.5	10.4	15.0
20	8.6	13.3	19.4
40	10.2	15.5	22.8
100	12.4	18.5	27.5
200	14.1	21.2	
300	15.1	22.6	