



V S 5 5 曲げクリープ試験




2 3

	10.5MPa	14.0MPa	17.6MPa
0.02	4.7	6.7	10.7
0.05	4.7	6.8	11.1
0.10	4.7	6.9	11.5
0.15	4.8	6.9	11.9
0.50	4.8	7.2	13.4
1	4.9	7.4	14.6
2	4.9	7.7	16.1
4	5.0	8.0	18.3
8	5.1	8.5	21.4
20	5.3	9.2	28.1
40	5.4	9.8	36.3
100	5.7	10.9	55.1
200	6.0	11.9	95.5
300	6.3	12.7	



4 0

	6.0MPa	9.0MPa	12.0MPa
0.02	2.2	4.1	5.4
0.05	2.3	4.1	5.5
0.10	2.3	4.2	5.5
0.15	2.4	4.2	5.6
0.50	2.4	4.4	4.8
1	2.5	4.5	6.1
2	2.6	4.7	6.6
4	2.8	5.1	7.3
8	3.1	5.6	8.2
20	3.8	6.7	10.3
40	4.6	8.1	12.6
100	6.1	10.8	16.8
200	7.5	13.1	19.6
300	8.5	14.6	



6 0

	2.3MPa	3.4MPa	4.5MPa
0.02	0.6	1.1	1.8
0.05	0.6	1.2	1.8
0.10	0.6	1.2	1.9
0.15	0.6	1.3	2.0
0.50	1.1	2.7	2.8
1	2.2	5.6	4.9
2	4.0	7.5	8.9
4	6.0	9.7	13.2
8	8.0	12.2	17.2
20	10.5	15.6	22.6
40	12.5	18.2	26.8
100	15.3	22.2	32.6
200	17.5	25.2	
300	18.9	27	