



# V S 7 4 3 曲げクリープ試験




2 3

	12.6MPa	16.8MPa	21.0MPa
0.02	5.7	8.2	11.2
0.05	5.8	8.3	11.9
0.10	5.8	8.4	12.6
0.15	5.8	8.5	13.1
0.50	5.9	8.9	15.2
1	6.0	9.2	16.7
2	6.1	9.5	18.8
4	6.2	10.0	21.7
8	6.3	10.5	26.1
20	6.5	11.6	35.3
40	6.7	12.6	46.3
100	7.2	14.2	73.1
200	7.6	16.0	117.3
300	7.9	17.2	



4 0

	7.0MPa	10.5MPa	14.0MPa
0.02	2.9	4.6	7.1
0.05	2.9	4.7	7.4
0.10	3.0	4.9	7.6
0.15	3.0	5.0	7.7
0.50	3.1	5.2	8.2
1	3.2	5.4	8.7
2	3.3	5.6	9.3
4	3.5	6.0	10.2
8	3.7	6.6	11.5
20	4.4	7.9	14.0
40	5.1	9.3	16.8
100	6.6	11.8	21.3
200	7.9	14.1	25.3
300	8.8	15.5	



6 0

	2.7MPa	4.0MPa	5.3MPa
0.02	0.7	1.2	1.7
0.05	0.7	1.4	2.4
0.10	0.8	1.4	2.6
0.15	0.8	1.6	2.7
0.50	1.2	2.3	3.8
1	1.8	3.2	5.3
2	2.9	4.6	7.5
4	4.1	6.3	10.0
8	5.4	8.0	12.6
20	6.9	10.4	16.0
40	8.1	12.1	18.6
100	9.7	14.4	22.1
200	11.0	16.2	
300	11.4	17.3	